

Dept: \_\_\_\_\_  
 No. : \_\_\_\_\_  
 Re. : \_\_\_\_\_  
 Telephone: 064/ 3396222-3396333-3397222  
 Ismailia  
 Fax.: 002/064/ 3914784 / 3914785  
 Email.: [info@suezcanal.gov.eg](mailto:info@suezcanal.gov.eg)

الإسماعيلية - في  
 إدارة: التخطيط والبحوث (مركز الأبحاث)  
 رقم القيد : \_\_\_\_\_  
 رقم الملف: \_\_\_\_\_  
 تليفون: 064/ 3397222 - 3396232 - 3396222 الإسماعيلية  
 فاكس: 002 / 064/ 3914785 - 3914784  
 بريد الكتروني: [info@suezcanal.gov.eg](mailto:info@suezcanal.gov.eg)

## عملية: إختبارات معملية على عينات GFRP

=====

السادة / شركة تيراتيكت للحلول البيئية.

تحية طيبة وبعد،،،

نتشرف بأن نرفق طيه نتائج إختبارات معملية على عينات GFRP المأخوذة بمعرفتكم من موقع المشروع عاليه والمسلمة لمركز الأبحاث بتاريخ 17/11/2025.

كود التقرير : Mat./1196/2025

ومرفق معه كشف بالتكاليف.

وتفضلوا بقبول فائق الاحترام ،،،

ق. مدير إدارة التخطيط والبحوث

د. أخصائي

( فتحي عبد الباري )

F-17-06 إصدار 2

إدارة التخطيط والبحوث	
صادر رقم : 192213	بتاريخ : 2025-12-07
<input type="checkbox"/> قسم المعنومات	<input type="checkbox"/> وحدة الأمراد
<input type="checkbox"/> قسم التخطيط	<input type="checkbox"/> وحدة الحسابات
<input checked="" type="checkbox"/> مركز الابحاث	<input type="checkbox"/> الخطوط الطويلة
<input type="checkbox"/> الوحدة الإقتصادية	<input type="checkbox"/> السكرتارية الرئيسية



Dept :  
No. :  
Re. :  
Telephone : 064 / 3910000 / 30 Ismailia  
Fax : 02 / 064 / 3914784 - 3914785  
Email : info@suezcanal.gov.eg

الإسماعيلية  
إدارة التخطيط والبحوث والدراسات (مركز الأبحاث)  
رقم الملف  
رقم الملف  
تليفون : ٣٠ / ٣٩١٠٠٠٠ / ٠٦٤ خط الإسماعيلية  
فاكس : ٣٩١٤٧٨٤ - ٣٩١٤٧٨٥ / ٠٢ / ٠٦٤  
بريد إلكتروني : info@suezcanal.gov.eg

الموضوع: كشف تكاليف تجارب معملية رقم ٨٢٨  
عملية: إختبارات معملية على عينات GFRP.  
الجهة الطالبة: شركة تيراتيک للحلول البيئية.  
على حساب: شركة تيراتيک للحلول البيئية.  
البطاقة الضريبية: ٥٧٧-١٣٠-٨٤٦  
بند الخصم: ٧٦٠/٢/١٠٠

م	البند	البيان	الكمية	الفئة (جنية)	التكلفة (جنية)	ملاحظات
١	ثالثاً-أ-٣-١٣	إختبار قوة التماسك بين الحديد والخرسانة	٣	٥٠٠,٠	١٥٠٠,٠	
٢	ثالثاً-ث-١١	تقرير فنى للإختبارات المعملية والحقلية	١	٦٠٠,٠	٦٠٠,٠	

إذن دفع : (٥٩٨)  
تكاليف التجارب: ٢١٠٠,٠  
١٤% ضريبة القيمة المضافة: ٢٩٤,٠  
إجمالي التكاليف: ٢٣٩٤,٠

رئيس مركز الأبحاث  
د. مهندس

( أحمد حسن أمين )


مهندس المعمل

- صورة لوحدة حسابات الإدارة لإتخاذ اللازم.



إدارة التخطيط والبحوث والدراسات  
مركز الأبحاث

اختبارات معملية على عينات GFRP



نوفمبر ٢٠٢٥

(2025/Mat./1196)

Suez Canal Authority  
Planning, Research, and Studies Department  
Research Center

Egypt, Ismailia  
P.O. box 41515 Ismailia

(+2064) 3396847 fax (+2064)3396848

[Research.Center@suezcanal.gov.eg](mailto:Research.Center@suezcanal.gov.eg)  
[www.suezcanal.gov.eg](http://www.suezcanal.gov.eg)

Code No. 2025/Mat/1196  
Dated Nov.27, 2025

APPROVED BY  
Head of Research Center  
Ahmed Hassan Amin

**TEST REPORT**  
**Glass Fiber Reinforced Polymers**

*Testing of composite fiberglass reinforcement of AKC grade of  $\varnothing 12$  mm  
compliance with ASTM D7205-21 requirements*


*(According to ECP 208-2019)*

*Egyptian code for Design Principles and construction Requirements*

*For the use of Fiber Glass-Reinforced Polymers in construction*


Prepared by: Eng. Mahmoud Mamdouh Zakaria

Signature.



Reviewed by: Dr. Eng. Omaila Mostafa Hamed

Signature.



Approved by: Eng. Karem Farouk Ibrahim

Signature.



Ismailia Governorate

2025

**LIST OF EXECUTORS**

**The Manufacturer: TERRA TECH Environmental Solutions, L.C.C. company**

**Test Supervisor**

Deputy Manager:  
Eng. Karem Farouk Ibrahim

Signature.



Head of Soil Research Division:  
Omaima Mostafa Hamed

Signature.



**Test Executors:**

Assistant Manager of Works:  
Mahmoud Mamdouh Zakaria

Signature.






TABLE OF CONTENTS

INTRODUCTION.....	1
TEST RESULTS.....	2
I. SAMPLE DIMENSIONS.....	2
II. PULL OUT TEST.....	3

@mahmoud.mamdoh/10344

## INTRODUCTION

- The tests have been performed upon an order of TERRA TECH.
- Tested object: Fiberglass reinforcement of AKC grade of 12 mm diameter.
- Address of the manufacturer of the tested objects: Investment Zone in Mit Ghamr
- Name of the manufacturer of the tested objects: TERRA TECH, LLC.
- Sampling reports (number, date): No. 2025/Mat./1196 dated Nov. 27, 2025.
- Test purpose: Determination of the physical and mechanical characteristics of GFRP reinforcement using the concrete pull-out test, in order to verify compliance with the requirements of ECP 208-2019 "Composite polymer reinforcement for armoring concrete structures. General specifications".
- Physical and mechanical characteristics to be determined:
  - Nominal diameter and actual cross-sectional area of the bar.
  - Bond strength between the GFRP bar and concrete under axial loading.
  - Failure mode, including identification of the type and location of failure (e.g., bar pull-out, concrete splitting, or bar rupture)
- Reference documents for testing methods:
  - ECP 208-2019 "Composite polymer reinforcement for armoring concrete structures. Methods of determining physical and mechanical characteristics"
  - ECP 208-2019 "Composite polymer reinforcement for armoring concrete structures. General specifications".




## TEST RESULTS

### I. Samples Dimensions

- Sample tagging – fiberglass reinforcement of 12 mm grade;
- Name of organization conducting the tests – Suez Canal Authority Research center;
- Test date – 17.11.2025;

Table (1) shows the dimensions of the specimens used.

**Table No. (1): The Samples Dimensions**

Items		Results			Samples shape
		(1)	(2)	(3)	
Concrete	Height (mm)	302	301	299	
	Diameter (mm)	150	150	150	
GFRP	Diameter of the GFRP bar (mm)	12	12	12	
	Embedded length of the GFRP bar inside the concrete (mm)	200	200	200	
	Exposed (free) length of the GFRP bar at the middle (mm)	151	153	154	
The steel cylinder	Length (mm)	250	255	254	
	Diameter (mm)	22	22	22	

*ahmed*

*Imaima*

*[Signature]*

## II. Pull Out Test

- Test date - 17.11.2025.
- The specimens were loaded at a constant rate until it reached its maximum load.

Table (2) shows the test results, and Figures (1 to 3) illustrate the test outcomes.

**Table No. (2): Test Results**

Sample No.	Failure Load (ton)	Bond Stress (kg/cm <sup>2</sup> )	Failure Mode
1	7.19	95.4	Concrete splitting failure
2	5.84	61.2	
3	6.65	108.6	
<b>Average</b>	<b>88.4</b>	<b>6.56</b>	




Figure (1): Bond strength test results for specimen No. (1)




Figure (2): Bond strength test results for specimen No. (2)




Figure (3): Bond strength test results for specimen No. (3)

*Ahmed*

*Imam*

*[Signature]*